



Technomelt Supra High-Performance hotmelt range for your packaging applications.

- » **High-quality results**
- » Excellent bond strength
- » Less maintenance effort, less downtimes thanks to extremely thermostable adhesive formulations
- » Average consumption up to 30% lower than conventional hotmelts
- » Outstanding cold flexibility and heat resistance

Technomelt Supra High-Performance hotmelt range for your packaging applications.

The Technomelt Supra range from Henkel with its powerful specialty adhesives is the product family that sets benchmarks in the adhesives industry when it comes to meeting your special needs regarding bond strength, mileage, application costs, and safety.

- » Higher mileage
- » Clean processing
- » Less maintenance
- » Shorter downtimes
- » Less waste
- » Less complexity
- » Resource-conserving adhesive solution

	Application:	Viscosity: <i>Brookfield at 160°C</i>	Open time:	Optimal processing temperature:
Technomelt Supra 60 Plus	Multi-purpose	1100 – 1500 mPas	Short	160 – 190 °C
Technomelt Supra 100	Multi-purpose	1200 – 1600 mPas	Short to medium	160 – 190 °C
Technomelt Supra 100 Plus-22	Multi-purpose, fast setting	1000 – 1700 mPas	Short to medium	160 – 190 °C
Technomelt Supra 120	Fast setting and low viscosity	450 – 800 mPas	Short to medium	140 – 180 °C
Technomelt Supra 100 Cool 	Low application temperature, high tack	1000 – 1500 mPas <i>(at 100 °C)</i>	Short	100 – 125 °C
Technomelt Supra 130 Cool	Low application temperature, high tack	1100 – 1500 mPas <i>(at 130 °C)</i>	Short	130 – 150 °C
Technomelt Supra 145 Plus	Multi-purpose, high thermal stability, good cold flexibility and excellent mileage	1150 – 1550 mPas	Short to medium	150 – 190 °C
Technomelt Supra 150 Plus	High heat resistance	1900 – 2500 mPas	Short to medium	160 – 190 °C
Technomelt Supra 300 HT	Deep-freeze applications	1400 – 1800 mPas	Medium	160 – 190 °C
Technomelt Supra 325 HT	High adhesion and long open time	1800 – 2600 mPas	Medium to long	160 – 190 °C
Technomelt Supra 350 HT	High adhesion	1800 – 2600 mPas	Medium	160 – 190 °C
Technomelt Supra 1000	Multi-purpose, New Hotmelt Generation	1600 – 1900 mPas	Short to medium	150 – 190 °C

Try Technomelt Supra now!

To experience how our Technomelt Supra range can improve your packaging operation, please contact your local sales representative for more information and trial assistance.

Scan vCard:



Henkel AG & Co. KGaA
40191 Duesseldorf, Germany
Phone: +49 211 797-4140
Fax: +49 211 798-2312
Email: eol@henkel.com
www.henkel.com/technomeltsupra

